



YachtCoatings

# TEMPEST

## TECHNICAL DATA SHEET

### Product description

Paint stripper for antifouling and monocomponent products. Tempest is not excessively dangerous. Easy to apply, it can be used on various surfaces: wood, metal, fiberglass and plastic. The product does not damage the gelcoat and does not affect epoxy primers. It is free from noxious chemical compounds and it does not produce toxic vapours.

### Product information

Aspect	Tixotropic coloured paste		
Colour	Light blue .001		
Specific gravity	UNI EN ISO 2811-1	1,10 ÷ 1,15 g/cm <sup>3</sup>	
Flash point	UNI EN ISO 13736	20 °C	
VOC (calculated average content)	ISO 11890-2/2006	305 g/l	
Packaging	2,5 Lt		

### Application and use

#### SURFACE PREPARATION

Apply on the surface at least 2 - 3 mm of this product and allow to react from 2 to 3 hours according to the external temperature. The surface must not be exposed to sunlight. Remove the soft mixture of TEMPEST and varnishes with a scraper or with high pressure water. If necessary, repeat the operation. Before painting, the surface must be thoroughly washed with fresh water and left to dry, sandpaper with paper Grit 180 - 220. Rinse and leave to dry for at least 24 hours.





YachtCoatings

# TEMPEST

## TECHNICAL DATA SHEET

### Application data

Application methods	 
Theoretical coverage	2 - 3 m <sup>2</sup> /l

### CONDITIONS DURING APPLICATION

During application and during the reaction time, the ambient temperature must not be lower than 5°C and must not be higher than 30°C.

Make sure there is enough ventilation when application takes place in closed environments.

### Storage

It is recommended to avoid exposure to air and extreme temperatures. To maximise the shelf life in the can, it is worth checking that the container is well closed during the storage and that temperature is between 10° C and 35° C. Avoid exposure to direct sunlight.



*YachtCoatings*  
**TEMPEST**  
TECHNICAL DATA SHEET

## Safety rules

---

Observe the provisions of DPR 303 and 547. Avoid the contact with the skin for example. Operate in well ventilated places and, if in closed areas, use vacuum cleaners, fans and air conveyors. During the application, use appropriate protections (masks, gloves, glasses, etc). Before using, read section 7-8 of the SDS.

### INSTRUCTIONS FOR THE DISPOSAL OF PRODUCTS AND PACKAGING

Empty packaging that contained products: Dispose of empty packaging according to the requirements of waste disposal law, for example by taking them to the recycling centre.

Packages containing the unused products: Disposal of the unused product in accordance with the law of disposal of such waste, for example by taking it to a recycling centre, recycling of packaging is prohibited in this case. Do not empty into drains or water courses. Product packaging must be kept indoor and temperature in the storage place must be between 10° C and 35 °C. Do not expose to sunlight.

## Notes

---

The values indicated in the present technical sheet can have slight variations from one batch to another. All data refer to the mixed product.

The applied product must not come in contact with water, chemicals or subjected to mechanical stress before the curing is complete. The above information is the result of accurate laboratory tests and practical experiences; however, since the product is predominantly used outside the manufacturer's control, Boero Bartolomeo S.p.A. Can only guarantee its quality. The information contained in this sheet may be subject to revision by the Company. For clarification, updates or for further information, it is recommended to contact Boero Bartolomeo S.p.A directly. The present datasheet annuls and replaces every other to this one.